

PRODUCT DESCRIPTION

The **EASYFit™** was developed to retrofit corroded or broken cast-iron vent pipes so that they could be properly flashed. Designed to be placed into the existing plumbing vent pipe, the **EASYFit™** creates a smooth surface on which to slide the **Ultimate Pipe Flashing®** over the new vent pipe to ensure a tight seal. Constructed from an inner core of rigid PVC that is overlaid with black Solarkote® cap stock. Providing the unmatched strength of PVC and the superior weatherability of acrylic. The integral cap forms a weathertight seal by employing an inner foam gasket seal. The **EASYFit™**, in combination with the **Ultimate Pipe Flashing®**, is the complete retrofit solution for Schedule 40 PVC DWV and cast-iron pipe flashings.

INSTRUCTIONS FOR USE / RECOMMENDATIONS

Cut the existing vent pipe (PVC DWV or cast-iron DWV) at or below the roof deck. The existing pipe must be cut low enough to make room for the **Ultimate Pipe Flashing®**. If cutting cast-iron pipe, use metal or diamond dust blade for cast-iron, cut slowly using low RPMs and oil the blade frequently. Cut the new **EASYFit™** to the desired length and then replace the ridged cap until it is flush with the newly cut pipe. It is recommended that once the existing pipe has been cut, add a thick bead of urethane caulk to the cut and then insert the **EASYFit™** until it rests securely in and on top of the old pipe.

BENEFITS

- Provides the ability to extend older DWV pipes
- Offers a new clean surface to install new flashing
- Cut to specific length, depending on existing vent pipe
- Improves overall appearance of old pipe vents
- Quick and simple solution
- 50-year warranty

3" and 4" CAST IRON SOLUTIONS				
CAST IRON PIPE	EASYSLEEVE® or EASYFIT™	EASY SLEEVE®	EASYFIT™	ULTIMATE PIPE FLASHING®
SLEEVE OVER EXISTING 3" CAST IRON PIPES				
3"	4" EasySleeve®	400		400
COMPLETE CAST IRON PIPE REPLACEMENT				
3"	3" EasyFit™		300	300
4"	4" EasyFit™		400	400



Specific Data



		<u>Nominal Value</u>	<u>Test Method</u>
Physical	Density	1.14g/cm ³	ISO 1183
	Melt Mass-Flow Rate (230 °C/3.8kg)	1.5g/10min.	ISO 1133
	Molding Shrinkage – Flow	3.0E-3 to 8.0E-3 in/in	ASTM D955
	Water Absorption E Equilibrium @ 73°F	0.40%	ISO 62
Mechanical	Tensile Modulus @ 73°F	215,000psi	ASTM D638
	Tensile Stress (break) @ 73°F	3,770psi	ISO 527-2
	Tensile Strain (break) @ 73°F	110%	ISO 527-2
	Flexural Modulus @ 73°F	174,000psi	ISO 178
	Flexural Stress @ 73°F	4,790psi	ISO 178
Impact	Notched Izod Impact @ 73°F	2.8 ft lb/in ²	ASTM D256
Hardness	Rockwell Hardness (R-Scale)	69	ASTM D785
Thermal	Heat Deflection Temp 264psi (1.8 Mpa)	126°F	ISO 75-2/A
Optical	Refractive Index ³	1.490	ISO 489
	Transmittance	90%	ASTM D1003
	Haze	2.0%	ASTM D1003
O.D. Sizing Availability for	Cast-Iron:	3" & 4"	
	Schedule 40 PVC:	3" & 4"	
Packaging	Six (6) per box with installation instructions in the box.		
Dimensions of Packaging	25" L x 11" D x 8" W	13lbs.	(EASYFit300)
	25" L x 14" D x 10" W	19lbs.	(EASYFit400)
Notes	All parts made and assembled in the U.S.A. UPF is a U.S. Patented Product Patent 9,228,689		

